

# EI-930 Ink

## HIGH VISCOSITY SILVER METAL COMPLEX CONDUCTIVE PASTE

### Product Highlights

- High viscosity silver metal complex paste designed for adhesion on a wide variety of surfaces
- Lead-free and halogen-free
- High electrical conductivity and thermal conductivity
- Low temperature curing
- Strong adhesion to PET, ITO, glass, PVDF, PI, silicon

**Table 2-Typical Electrical Properties**

Curing Temp (°C)	Thickness (µm)	Resistivity (µΩ-cm)	Resistivity (mOPS*/mil)	% Bulk Silver (± 5%)
60	1.2	134	52.8	1.2
80	1.3	119	47.0	1.4
100	1.3	104	41.1	1.5
110	1.3	93	36.6	1.7
140	1.3	49	19.4	3.3
160	1.3	46	17.9	3.5
200	1.3	31	12.0	5.3
300	1.0	12	4.6	14.0

\*milliohms per square

### Examples of Ink Processing

#### Storage and Handling

- Store refrigerated at < -18 °C for periods > 8 hours. Ink can be left at room temperature for up to 8 hours.
- Prior to use, allow ink to come to room temperature and mix well using a spatula.
- Print and cure in a well-ventilated area.
- Clean up solvents: hydrogen peroxide, water.

#### Typical Process Parameters

- Screen: 325 mesh, EOM
- Pressure Parameters: 57 - 65N
- Squeegee Speed: 25 mm/sec
- Snap off: 1.8 - 2.0 mm
- Curing conditions: ramp from less than 60 °C → final curing temperature at 10 °C/min, hold at final curing temperature for 20 minutes
- Rinse of Screen: DI water followed by Ethanol or IPA

**Table 1-Typical Physical Properties**

Properties	Values
Viscosity	11,000 – 33,000 cP @ 2/s
Solid Content	29 wt%
Shelf life	6 months (at < -18 °C storage)

**Table 3-Typical Properties (cont.)**

Properties	Values
Adhesion (ASTM D3359)	5B on PET, ITO, glass, PVDF, SNW
Environmental Reliability Testing (85 °C/85 %RH)	Passed 1000 hrs of testing

*These properties have been measured during controlled experiments at our Electroninks laboratories. Details of these experiments are available upon request.*

*Disclaimer: The information provided in this Technical Data Sheet (TDS) is compiled in good faith and obtained using procedures performed at Electroninks and to the best of Electroninks's knowledge. The information on this TDS has been updated on the date printed, and latest versions can be obtained upon request. The customer is responsible for conducting tests to determine whether Electroninks's products are compatible with the customer's substrates and specific applications.*